

Amendments to the Claims

The following listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of the Claims:

Claims 1-21 (canceled)

22. (currently amended) A transparent, non-elastomeric, poly(thio)urethane/urea polythiourethane/urea material comprising the reaction product of:

- (a) at least one (α , ω)-diiso(thio)cyanate polysulfide prepolymer, said prepolymer being free from disulfide (-S-S-) linkage; and
- (b) at least one aromatic primary diamine, in an equivalent molar ratio amine function/iso(thio)cyanate function (NH_2/NCX , $\text{X}=\text{O}$, S) ranging from 0.5 to 2, said aromatic primary diamine being free from disulfide (-S-S-) linkage,


wherein the (α , ω)-diiso(thio)cyanate polysulfide prepolymer is the reaction product of at least one cycloaliphatic or aromatic (α , ω)-diiso(thio)cyanate and at least one ~~(α , ω)-diol~~ or (α , ω)-dithiol prepolymer, said ~~(α , ω)-diol~~ or (α , ω)-dithiol prepolymer being a polysulfide or a mixture of polysulfides.

23. (currently amended) The ~~transparent, non-elastomeric poly(thio)urethane/urea~~ material of claim 22, wherein the equivalent ratio NH_2/NCX ranges from 0.90 to 1.10.

24. (previously presented) The material of claim 22, wherein the equivalent ratio NH_2/NCX ranges from 0.93 to 0.95.

Claims 25-27 (canceled)


28. (previously presented) The material of claim 22, wherein the polysulfide or mixture of polysulfides is a polysulfide of formula:



in which x and y are chosen such that the two following conditions are simultaneously satisfied:







- the polysulfide of formula Ia is a prepolymer; and
- the number average molecular weight of the polysulfide of formula Ia is not more than 3000 gmol^{-1} .




29. (previously presented) The material of claim 22, wherein the aromatic diamine contains at least one S atom in its molecule.
30. (previously presented) The material of claim 29 wherein the diamine is selected from



in which R is H or an alkyl group and R' is an alkyl group, and mixtures of the above diamines.


31. (previously presented) The material of claim 22, wherein the material is the reaction product of:
- said at least one (α , ω)-diisothiocyanate polysulfide prepolymer;
 - said at least one aromatic primary diamine; and
 - at least one di-, tri-, or tetra alcohol, or at least one di-, tri-, or tetra thiol, or a mixture thereof.
32. (previously presented) The material of claim 31, wherein the alcohols and thiols are selected from the group consisting of:






and mixtures thereof.

33. (previously presented) The material of claim 22 having a refractive index, n_D^{25} , higher than 1.53.
34. (previously presented) The material of claim 22 having a refractive index, n_D^{25} , of at least 1.55.
35. (previously presented) The material of claim 22 having a refractive index, n_D^{25} , of at least 1.57.
36. (previously presented) The material of claim 22, wherein the polysulfide is an hyperbranched polysulfide resulting from the polymerization of a diepisulfide of formula:




in which R^1 and R^2 are, independently from each other, H, alkyl, aryl, alkoxy, alkylthio or arylthio, R^3 and R^4 are independently from each other,



Ra designates H, alkyl, aryl, alkoxy, aryloxy, alkylthio or arylthio, with 2-mercaptoethyl sulfide (DMES).


37. (previously presented) The material of claim 36, wherein the diepisulfide has formula :



38. (previously presented) An optical article made from a material according to claim 22.
39. (previously presented) The material of claim 48, wherein n' is such that the number average molecular weight (\overline{M}_n) of the prepolymer ranges from 650 to 1350 g mol⁻¹.


Claims 40-41 (cancelled)

42. (previously presented) The material of claim 30, wherein R and R' are CH₃.
43. (previously presented) The material of claim 30, wherein the diamine is a mixture of by weight:




Claims 44-46 (cancelled)

47. (previously presented) The material of claim 22, wherein the polysulfide or mixture of polysulfides is a prepolymer resulting from the polymerization of diepisulfides of formula:




in which R^1 and R^2 are, independently from each other, H, alkyl, aryl, alkoxy, alkylthio or arylthio; R^3 and R^4 are, independently from each other,



R_a designates H, alkyl, aryl, alkoxy, aryloxy, alkylthio or arylthio and, n is an integer from 0 to 4 and m is an integer from 1 to 6.

48. (previously presented) The material of claim 22, wherein the polysulfide or mixture of polysulfides is

a prepolymer of the formula:



where n' is such that the number average molecular weight (\overline{M}_n) of the prepolymer ranges from 500 to 1500 g mol⁻¹.

49. (previously presented) The material of claim 22, wherein the at least one (α , ω)-diiso(thio)cyanate polysulfide prepolymer has a number average molecular weight of not more than 3000 g mol⁻¹.